

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
16 October 2003 (16.10.2003)

PCT

(10) International Publication Number
WO 03/084982 A2

- (51) International Patent Classification⁷: **C07K 1/00** Berkett, Austin, TX 78745 (US). MCDADE, Ralph [I]; **
- (21) International Application Number: PCT/US02/36458
- (22) International Filing Date:
14 November 2002 (14.11.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/331,312 14 November 2001 (14.11.2001) US
- (71) Applicant (for all designated States except US): LUMINEX CORPORATION [US/US]; 12212 Technology Boulevard, Austin, TX 78727 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): LUGADE, Ananda, G. [IN/US]; 13528 Wyoming Valley Drive, Austin, TX 78729 (US). HOFFACKER, Kurt, D. [US/US]; 7800 San Felipe #1503, Austin, TX 78729 (US). JENKINS, Adam, J. [US/US]; 11160 Jollyville Road #324, Austin, TX 78759 (US). MICHAEL-BALLARD, Karri, L. [US/US]; 6280 McNeil Drive # 404, Austin, TX 78729 (US). PATSENKER, Leonid [UA/UA]; 60 Lenin Avenue, Kharkov, 61001 (UA). TERPETCHNING, Ewald [US/US]; 12440 Alameda Trace circle #1936, Austin, TX 78727 (US). THOMASON, veronica, D. [US/US]; 2526
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 03/084982 A2

(54) Title: FUNCTIONALIZED COMPOSITIONS FOR IMPROVED IMMOBILIZATION

(57) Abstract: The present invention relates to improved covalent coupling of two or more entities such as biomolecules, polymer compositions, organic/inorganic molecules/materials, and the like, including their combinations, through one or more novel reactive groups attached to linker groups of 2-1000 atoms length. The present invention also contemplates the use of bifunctional bridge molecules to link two or more entities, wherein the functional groups of the bridge molecules are the novel reactive groups of the present invention.

FUNCTIONALIZED COMPOSITIONS FOR IMPROVED IMMOBILIZATION**1. Cross Reference to Related Applications**

This application claims priority to U.S. provisional Application No. 60/331,312,
5 filed November 14, 2001, the disclosure of which is hereby incorporated herein by
reference in its entirety.

2. Field of the Invention

The present invention relates to improved covalent coupling of two or more
10 entities such as biomolecules, polymer compositions, organic/inorganic
molecules/materials, and the like, including their combinations, through one or more
novel reactive groups attached to linker groups of 2-1000 atoms length.

3. Background of the Invention

15 The immobilization of entities (such as enzymes, antibodies, proteins, DNA,
nucleotides, PNA, carbohydrates, fatty acids, lectins, peptides, receptors, chromophores,
fluorophores, chemiluminescent compounds, dendrimers, J or H aggregates, cells,
bacteria, viruses, whole prokaryotic or eukaryotic organisms, membranes (synthetic or
natural), fullerenes, nanotubes and the like) can be achieved by simple covalent reaction
20 with an activated solid surface. For example, particles (e.g., micro- and nano-spheres;
metal particles comprised of one or more metals with any size, shape, or composition; -
semiconductor particles, molecularly imprinted polymers (MIPS), magnetic particles; or
dyed materials) or microtiter plates are a common solid matrix in many immobilization
systems. Preparing and maintaining the active, functionalized surface is an important

factor to assure immobilization of sufficient biological material for development of a sensitive assay. Current immobilization procedures of biomolecules on solid surfaces generally involve reactions of an activated amino or carboxyl group derivatized solid surface with amino- or thiol-modified biomolecules. After activation, or after
5 introduction of a functionalized spacer, these groups offer direct attachment sites. Most of these functional groups (such as NHS esters, isothiocyanates, etc.) are prone to hydrolysis in an aqueous environment and become non-reactive (i.e., chemically inactive) in a matter of less than an hour.

Reactive or functionalized microspheres are conventionally produced via
10 copolymerization of suitably functionalized monomers, or via post-chemical modification of preformed microspheres. Post-functionalization is a popular method for preparing reactive particles as earlier described by Upson (J. Polym. Sci., Polym. Symp. 1985, 72, 45).

In the last three decades the advancements in the field of affinity chromatography,
15 solid-phase synthesis, and immobilization of bio-macromolecules, such as proteins, oligonucleotides and the like, have led to microsphere-based biomedical applications. More recent work on the production and evaluation of a variety of tailor-made particles has been reported by several groups including Margel *et al.*, (J. Polym. Sci. 1991, A-29, 347-355; Anal. Biochem. 1981, 128, 342-350), Ugelstad *et al.*, (Makromol. Chem. 1979,
20 180, 737-44; Adv. Colloid Interface Sci. 1980, 13, 102-140), and Rembaum *et al.* (Br. Polym. J. 1978, 10, 275-280; J. Macromol. Sci. Chem. 1979, A-13, 603-632). A review by R. Arshady, (Biomaterials, 1993, 14, 5-15) describes the synthesis and physico-chemical properties of reactive and labeled microspheres.

Assays based on fluorescent microspheres for multiplexed analysis have been reported by several groups (Fulton et al., Clin. Chem. 1997, 43, 1749-56; Kettman et al., Cytometry, 1998, 33, 234-43; McDade et al., Med. Dev. Diag. Indust. 1997, 19(4), 75-82; McHugh, Methods Cell Biol. 1994, 42, 575-95; Nikiforov et al., Nucleic Acid Res. 11994, 22, 4167-75; US/6,449,562; US/5,981,180; US/6,046,807; US/6,057,107; US/6,268,222; US/6,366,354; US/6,411,904; US/5,736,330; US/6,139,800).

Fray et al. have reported a strategy in which particles are pre-activated with hydrolysis-resistant aldehyde functional groups but low reaction yields of <8% have been observed with these microspheres (Bioconjugate Chem. 1999, 10, 562-71). Milton of Beckman Coulter, Inc. has reported a reaction between an acyl fluoride activated polymer-surface and an amino derivatized biomolecule at room temperature (USP 6, 146, 833; Nov. 14, 2000). The use of fluorophenyl resins in the solid phase synthesis of amides, peptides, hydroxamic acids, amines, urethanes, carbonates, sulfonamides and alpha-substituted carbonyl compounds has been published (WO 99/67228).

Medvedkin et al. have used sulfo-tetrafluorophenyl activated esters in peptide synthesis and demonstrated their reactivity combined with good stability under aqueous storage conditions (Bioorg. Khim. 1995, 21(9), 684-90). Apparently, the pre-activation of polystyrene surfaces with this reagent has not yet been reported prior to the present application.

Hoechst claimed the use of reactive vinyl sulfone (VS)-modified dyes for dyeing of cellulose and wool fibers in 1950 (DBP 960,534). A review by Siegel gives a complete account of reactive dyes based on vinyl sulfones (VS) and its protected 2-sulfatoethyl and 2-thiosulfatoethyl sulfones (E. Siegel in The Chemistry of Synthetic

Dyes Vol. VI, (Ed. K Venkataraman); 2-108, Academic Press, 1972). Sterling Winthrop Inc, has demonstrated modification of proteins with PEG-supported vinyl sulfone (U.S. Patent No. 5, 414, 135).


The most frequently used method to immobilize biomolecules (such as
5 oligonucleotides, proteins, or carbohydrates) onto fluorescent microspheres is by activating surface carboxy groups. The activation requires excess EDC and a coupling pH of 4 to 6. The reaction involves the intermediate formation of an activated O-acylurea derivative between the carbodiimide and carboxyl functions. A subsequent nucleophilic attack by the primary nitrogen of the amino-groups of the biomolecule brings about the
10 formation of the amide linkage with the release of the substituted urea. The optimum pH for the formation of O-acylurea is about pH 4-5. The intermediate has an extremely short half-life and rapidly undergoes hydrolysis or rearranges to give the N-acylurea adduct. The primary amino group of the nucleophile is predominantly protonated at about pH 4-5 and is thus mostly unreactive. These limitations can severely restrict coupling yields. At
15 low pH, the nucleic acid bases undergo intensive protonation. Such type of protonation induces a DNA melting that exposes the hydrophobic core of the helix, enhancing nonspecific hydrophobic interactions with the solid matrix. Despite these drawbacks, EDC-mediated coupling currently is the major mode of covalent immobilization of biomolecules to solid surfaces. (Hermanson, G. T. in Bioconjugate Techniques,
20 Academic Press; N. Y. 1996; Andreas Frey et. al., Bioconjugate Chem. 1999, 10, 562-71; Maxime A. Gilles et. al., Anal. Biochem., 1990, 184, 244-48; Vivien W. F. Chan et. al., Biochem. Biophys. Res. Communications., 1988, 151(2), 709-16; Ivan L. Valuev et al., Biomaterials, 1998, 19, 41-43.)

The citations of the various references described above and throughout this application are not to be taken as admissions that these references constitute prior art for the present invention. However, each of the cited references is incorporated in its entirety by reference in the present application.


5

4. Summary of the Invention


The present invention is based, at least in part, upon improved methods and compositions for covalent coupling of two or more entities (B, B', etc.) such as biomolecules, polymer compositions, organic and/or inorganic molecules and/or materials, etc., through one or more "novel reactive groups" (Structures 1-6). The illustrations and examples provided herein are not intended to limit the scope of the invention in any way.




1




2




3



4



5



6

15

Entities B, B', etc., under the present invention comprise, but are not limited to, glass, quartz, monomer, polymer, dendrimer, MIPS, membranes, metal, clay, diatomaceous earth, particle (dyed or undyed), particle (magnetic or non-magnetic), particle (micro- or
5 nanospheres), fullerenes, nanotubes, biomolecule, chromophore, fluorophore, chemiluminescent compound, semiconductor particles, semiconductor nanocrystals (quantum dots), J- or H- aggregates, cells, organisms, bacteria, viruses, or any combination thereof. Entities B, B', etc., can be the same or different, and can be functionalized or non-functionalized.

10 The novel reactive groups of the present invention are conjugated to entities B, B', etc., by way of a linker, $(L)_n$, where L is a hydrocarbon linker with n number of atoms (e.g., 2 to 1000) of H, C, O, N, Si, P and S in straight or branched chains, rings, or combinations thereof.

 In some embodiments, one or more entities B, B', etc., are nucleophile-containing
15 entities, *i.e.*, they contain hydroxyl, amine, thiol...etc., groups, or the entities are conjugated to such groups. In such cases, attachment of the novel reactive groups may be accomplished by the chemical reaction of the electrophilic reactive group of one or more of Structures 1-6 with the nucleophilic group contained on or within the entity. Such chemical reactions include, but are not limited to, nucleophilic addition or nucleophilic-
20 based reaction known to a person of ordinary skill in the art, substitution and/or displacement.

 By way of a non-limiting example, a reaction of the present invention whereby two entities, B and B', are cross-linked via one or more of Structures 1-6. Any

nucleophile- or electrophile-containing groups are termed A, A', etc., where A and/or A' are a novel reactive group, or combination thereof, discussed in the present invention and/or a nucleophile (e.g., alcohol, amine, thiol...etc.), respectively. A and A' can be the same or different novel reactive group and/or the same or different nucleophile. B and B' can either be the same and/or different entities. Several possible combinations of such elements are discussed, below.


In one embodiment, one entity B, a polymeric microsphere, is conjugated with an electrophile-containing group of one of Structures 1-6 through the group's respective linker R₁-R₆. A second entity, B', a semiconductor nanoparticle, is conjugated with a nucleophilic group at its surface. A straightforward nucleophilic substitution reaction results in the linking of B with B' by way of the linker.

In yet another embodiment of a reaction linking B and B', where A and A' are both novel reactive groups of Structures 1-6, or a combination thereof, a bifunctional linker or bridge molecule is used to covalently couple the two or more entities. In one such embodiment, the bifunctionality of the linker is nucleophilic (e.g., amine, thiol, etc.). In other words, the bridge molecule contains two or more nucleophilic groups, one of which reacts with each of A and A' such that B and B' are linked through the combined length of the linker arms of A and A' and the length of the bridge molecule.


In yet another embodiment, B and B' contain A and A', respectively, which are both nucleophiles. In this embodiment, a bifunctional linker or bridge molecule is used to couple the two or more entities whereby the bifunctionality of the linker or bridge molecule are one or more novel electrophilic reactive groups of Structures 1-6, where those groups can be the same or different novel reactive groups. The bridge molecule

may or may not be constructed by joining the free ends of the linkers R_1 - R_6 of the respective electrophilic reactive groups of Structures 1-6. Following the reaction of these elements, B and B' are linked via the bifunctional bridge molecule binding covalently to their respective nucleophilic groups. In another version of this embodiment, if A and A' are both nucleophiles, then a bifunctional linker or bridge molecule is used to couple the two or more entities wherein C and/or C' are a functional group or groups (e.g., NHS ester, isothiocyanate, sulfonyl chloride, etc.) known to react with nucleophiles A and A'. C and C' can be the same or different functional groups which are attached to the linker or bridge molecule by way of one or more (n) novel electrophilic reactive groups of Structures 1-6 where n is the number of novel electrophilic reactive groups.


In particular, the present invention is directed toward novel conjugated compositions comprising one or more, in any combination, of Structures 1-6:




1



2



3



wherein:

n is 0, 1, 2, or 3;

X and Y are oxygen and/or sulfur in any combination;

5 X₂ and X₃ are one or more halogens, preferably chlorine or fluorine;

Y₂ is nitrogen or carbon;

arom is a substituted or unsubstituted phenyl, naphthyl or other polycyclic aromatic ring structure;

10 Z is a halide, preferably chloride or fluoride, 2,3,5,6-tetrafluoro-4-sulfo-phenoxide, N-hydroxysuccinimide or other electrophilic (nucleofugal) group;

and

R₁-R₆ are hydrocarbon linker groups containing from 2-1000 atoms, optionally containing one or more halogen or heteroatoms selected from the group consisting of O, N, Si, P and S; in straight or branched chains, rings, or combinations thereof; and

15

wherein the one or more, in any combination, of Structures 1-6 are connected through their respective linker groups, R₁-R₆, to at least one entity B, wherein B is:

a 2-D film or substrate;

a micro- or nano- particle of any size or shape composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal, semiconductor particle, semiconductor nanocrystal, magnetic particle, fullerene, nanotube, or any combination thereof;

20

an enzyme, antibody, protein, DNA, RNA, nucleotide, PNA, carbohydrate, fatty acid, lectin, peptide, receptor, dendrimer, cell, bacteria, virus, whole prokaryotic or eukaryotic organism, synthetic or natural membrane, biotin, hapten, organic monomer or polymer, or any combination thereof;

5 a chromophore, fluorophore, bio- or chemi-luminescent compound, J or H aggregate;

one or more of Structures 1-6 connected through their respective linker groups R_1 - R_6 ; or any combination thereof.

In yet another further embodiment, the present invention is directed to novel
10 compositions as described above wherein R_1 - R_6 contain 2-100 atoms, or more preferably wherein R_1 - R_6 contain 2-10 atoms.

The present invention also encompasses compositions comprising the Structures 1-6 noted above, wherein R_1 - R_6 comprise hydrocarbon linker groups containing, optionally, one or more halogen or heteroatoms selected from the group consisting of O,
15 N, Si, P and S; in straight or branched chains, rings, or combinations thereof containing from 2-1000 atoms, preferably 2-100 atoms, or more preferably wherein R_1 - R_6 contain 2-10 atoms.

The present invention also is directed toward compositions as described above wherein B is a polymeric microsphere or nanosphere. Even more preferred is an
20 embodiment wherein the polymeric microsphere further comprises polystyrene/divinyl benzene and/or carboxyl functional groups at least on its surface, and even more preferred is an embodiment wherein the microsphere further comprise one or more fluorescent dyes in distinguishable ratios.

As noted above, the present invention relates, in a preferred embodiment, to functionalized microspheres. A series of reactive functional groups has been evaluated on polystyrene-based microspheres for their ability to immobilize biomolecules, which biomolecules comprise prokaryotic or eukaryotic cells, transgenic cells, organisms, bacteria, viruses, plasmids, expression vectors, enzymes, proteins, fusion proteins, antibodies, chimeric antibodies, DNA, RNA, PNA, fatty acids, lectins, peptides, and receptors, or any combination thereof. Activated oxocarbon acids (e.g., mono-fluoro squaric acid (MFS)), tetra-fluoro-sulfophenyl ester (TFS), vinyl sulfone (VS), dihaloquinoxaline, sulfonyl fluoride, cyanuric acid halide and halopyrimidine show improved performance for immobilizing biomolecules as they (a) spontaneously react with nucleophilic groups of biomolecules, (b) show substantially improved stability in aqueous media, (c) form stable conjugates with biomolecules, (d) require no additional activating reagents and (e) may provide more specific conjugation (i.e., reduced non-specific interaction/binding with solid substrates) thus protecting the integrity of the biomolecule.

In yet another embodiment, a novel reactive group can be attached first to a biomolecule and then coupled to a solid support containing nucleophilic groups. Also disclosed are new linker systems aimed at improving the coupling yields of biomolecules to solid surfaces.

In particular, the present invention is directed toward a method for coupling two or more entities together by providing one or more conjugate compositions as described above having one or more, in any combination, of Structures 1-6 connected through their

respective linker groups, R_1 - R_6 , to at least one entity B; providing one or more nucleophile-containing entities comprised of:

a 2-D film or substrate;

a micro- or nano-particle of any size or shape, composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal (including semiconductors, semiconductor nanocrystals, and magnetic particles), fullerene, nanotube or any combination thereof;

an enzyme, antibody, protein, DNA, RNA, nucleotide, PNA, carbohydrate, fatty acid, lectin, peptide, receptor, chromophore, fluorophore, bio- or chemiluminescent compound, J or H aggregate, cell, bacteria, virus, whole prokaryotic or eukaryotic organism, synthetic or natural membrane, biotin, hapten, organic monomer or polymer, or dendrimer, or any combination thereof; and

reacting the one or more conjugate compositions with the one or more nucleophile-containing entities to produce at least one entity B linked through one or more linker arms of Structures 1-6 to said one or more nucleophile-containing entities.

In another embodiment, the present invention encompasses a method for the synthesis of compositions of noted above wherein the one or more, in any combination, of Structures 1-6 are conjugated to the entity B before the fabrication of the entity B; during the fabrication of the entity B; are conjugated to the entity B after the fabrication of entity B.

Another preferred embodiment of the present invention is directed toward a method of crosslinking one or more nucleophilile-containing entities comprising reacting a composition of Structure 1, as described above, wherein:

(a) n is 0, 1, 2, or 3

5 (b) X and Y are oxygen and/or sulfur in any combination;

(c) Z and R₁ are halogen (including chloride and fluoride); 2,3,5,6-tetrafluoro-4-sulfo-phenoxide; N-hydroxysuccinimide; and similar nucleofugal groups or any combination thereof;

with one or more nucleophile-containing entities, comprised of:

10 a 2-D film or substrate;

a micro- or nano-particle of any size or shape, composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal (including semiconductors, semiconductor nanocrystals, and magnetic particles), fullerene, nanotube or any combination thereof;

15 an enzyme, antibody, protein, DNA, RNA, nucleotide, PNA, carbohydrate, fatty acid, lectin, peptide, receptor, chromophore, fluorophore, bio- or chemiluminescent compound, J or H aggregate, cell, bacteria, virus, whole prokaryotic or eukaryotic organism, synthetic or natural membrane, biotin, hapten, organic monomer or polymer, or dendrimer or any combination
20 thereof;

to provide one or more crosslinked nucleophile-containing entities.

In yet an even further embodiment, the present invention is directed toward the use of Structures 1-6 in the creation of bridge molecules for linking two or more entities

together, or compositions comprising one or more of Structures 1-6 as bridge molecules. Various embodiments of the present invention include multifunctional bridge molecules of two or more of Structures 1-6 joined through their respective linker groups R_1 - R_6 , in an end-to-end fashion, in a branched chain, or in dendritic fashion. Such bridge
5 molecules may be used to link together covalently two or more entities having nucleophilic groups by straightforward chemical reactions such as nucleophilic addition or substitution or any other applicable chemical reaction known to a person of ordinary skill in the art.

In yet another variation of this invention, a multifunctional bridge molecule is
10 provided wherein the functional groups are one or more of Structures 1-6 and one or more nucleophilic groups. Such bridge molecules may be used to link together covalently one or more entities having nucleophilic groups with one or more entities conjugated to one or more of Structures 1-6 by straightforward chemical reactions such as nucleophilic addition or substitution, wherein the entity(ies) having nucleophilic
15 groups react with the bridge group functionality(ies) of Structures 1-6, and the entity(ies) having reactive groups of Structures 1-6 react with the nucleophilic bridge group functionality(ies) to yield two or more entities linked together.

Compositions of such multifunctional bridge groups are also envisioned. A bridge group composition is envisioned wherein one or more of Structures 1-6, in any
20 combination, are conjugated by their respective linker groups R_1 - R_6 to one or more nucleophilic groups, wherein if two or more of Structure 1-6 are joined together, they are joined together through their respective linker groups R_1 - R_6 , wherein the joining is one or more of end-to-end, branched, or dendritic, in any combination.

5. Brief Description of the Figures

Figure 1 shows a comparison of the COOH-functionalized microsphere, EDC coupling method (A) to mono-fluoro squaric acid-functionalized microspheres (MFS) (B) over time (accelerated at 25°C). The novel pre-activated microspheres (B) provide more reproducible coupling day-to-day than the standard EDC-mediated reactions (A).

Figure 2 shows a stability study of vinyl sulfone (VS)-functionalized microspheres stored in buffer, pH 6 at 4°C.

Figure 3 shows an accelerated stability study of mono-fluoro squaric acid (MFS)-functionalized microspheres stored dry.

Figure 4 shows an accelerated stability study of mono-fluoro squaric acid (MFS)-functionalized microspheres stored dry over a longer time period than shown in Fig. 3.

Figure 5 shows an accelerated stability study of tetra-fluoro-sulfopheyl ester (TFS)-functionalized microspheres stored dry.

Figure 6 shows an accelerated stability study of vinyl sulfone (VS)-functionalized microspheres stored dry.

Figure 7 shows a coupling titration of an amino-functionalized DNA probe on (A) COOH-functionalized microspheres (EDC-mediated reaction) vs. (B) mono-fluoro squaric acid (MFS)-functionalized microspheres (spontaneous reaction) methods. Both coupling titrations were performed at 25°C. The DNA complement target concentration for the assay was 20 fmoles at a hybridization temperature of 55°C. The COOH-EDC method (A) yields a non-linear response to the amount of probe coupled to the microspheres. The mono-fluoro squaric acid-functionalized microsphere's probe titration

(B) is more linear. These results are reproducible and may be the result of a more specific coupling. Note: 25°C is not an optimal coupling temperature for the mono-fluoro squaric acid-functionalized microspheres. Signal is expected to improve with optimization of all parameters.

5

6. Detailed Description of the Preferred Embodiments

6.1 Functional Groups

Because of the shortcomings of current coupling methods - lack of stability or
10 inability to spontaneously react with biomolecules in aqueous media or both - the inventors decided to introduce hydrolysis-resistant, ready to use, pre-activated microspheres, for the immobilization of biomolecules. Table 1 is a partial, non-limiting, list of such novel reactive microspheres.

Sulfonyl fluorides are known to be more stable in an aqueous environment than
15 sulfonyl chlorides (Table 1, 1a - 1d) and the aromatic versions are more stable as compared to their aliphatic counter parts. Several routes starting either from acids or acid chlorides were used to synthesize sulfonyl fluorides (Table 1, 2a - 2e) on the surface of polystyrene microspheres.

The cyclic oxo-carbon acids (deltic, squaric, croconic and rhodizonic) have two
20 acid equivalents and 1-4 carbonyl groups in a ring. The inventors have used one of the acid equivalents to connect the ring to one of our linker molecules and activated the other to a reactive derivative. Several routes to synthesize squaric acid derivatized microspheres are provided in Table 1 (-3a - 3e). The resulting activated beads are very

reactive with amine containing molecules and can be stored on a long term basis if kept dry. This class of reactive group can also be used as a replacement for NHS esters and the like to activate dyes and biomolecules.

Cyanuric fluoride can react with up to three equivalents of amine, replacing the
5 fluorine atoms with the nitrogen atoms of the amines. The inventors have isolated microspheres in which cyanuric fluoride was reacted with one equivalent of an amine linker, which was attached to a microsphere (Table 1, 4). The second and third fluorine are still available for reaction with bio-molecules. Related molecules such as cyanuric chloride, 2,4,6-trichloro pyrimidine or 2.4.6-trifluoropyrimidine are used similarly.

10 Vinyl sulfone (VS) microspheres were generated by reacting divinyl sulfone with microspheres containing hydroxy, amino or thiol groups (Table 1, 5a - 5b). The remaining vinyl moiety is available for reaction with both thiols and amines. This group is less susceptible to hydrolysis, but requires a basic pH for reaction with amines. The vinyl sulfone (VS) group can be protected from oxidation during long term storage by
15 reacting it with sodium thiosulfate as in Table 1, 5c. The vinyl moiety is regenerated at about pH 9-10.

Perfluorinated phenols have been developed as hydrolysis resistant replacements for N-hydroxysuccinimide for conventional coupling chemistries. The inventors reacted tetrafluoro-phenolsulfonic acid with carboxylic acid groups directly on the surface of
20 microspheres (Table 1, 6) or on the end of a linker molecule. Fluorine atoms provide the moiety with a good leaving group and the sulfonic acid maintains the charge on the surface of the microsphere, which is needed to disperse it in water.

6.2. Linkers

The overall performance of a functionalized microsphere is controlled by several parameters - microsphere charge, density of cross-linking, location, accessibility
5 and chemical stability of functional groups, length, charge and nature of the linker group.

Linkers play an important role in bioconjugations. They are selected based not only on their length, but their chemical nature. The overall nature of the linker is known to govern the overall hydrophilicity or hydrophobicity of the reagent environment. It is well understood that extended linkers can reduce the steric interferences between the
10 analyte and the solid matrix.

Several different classes of linkers could be used to connect the above mentioned functional groups to microspheres. Examples of these linkers are shown in Table 2.

Ethylene glycol based linkers (Table 2, 1 - 3) are surface modifiers which are known for improving the stability of hydrophilic surfaces. Additional stability is ensured
15 by replacing CH_2 with CF_2 .

Diamines and hydrazides are known to provide hydrophobic surfaces (Table 2, 5 - 8). Polyethylenimines (Table 2, 9) exhibit a 'proton sponge' effect, which can be used to control the surface charge of the microsphere. Polyamides and polysulfonamides (Table 2, 10 -13) contain acidic protons with a pKa of about 1-2. These linkers, therefore,
20 provide polyanions at physiological pH and hence provide long storage stability. Dendrimers or highly branched linkers (Table 2, 14) are known to adopt to well defined morphologies and provide a kind of encapsulation to the reactive groups and hence protect them from hydrolysis. DTPA (diethylenetriamine pentaacetic acid) linkers (Table

2, 15) provide multiple carboxylates. These type of linkers are known to form stable metal complexes. Polyacrylic acid and polylysine chains (Table 2, 16 - 17) can be introduced to improve the degree of immobilization.

5 6.3. Examples of Specific Application

The following are examples of specific applications of the present invention. These examples are not intended to limit the scope of the invention in any way.

10 Example 6.3.1

This example relates to, but is not limited to, the use of functionalized, or pre-activated, microspheres for covalent immobilization of biomolecules.

- 15 (a) A solid support comprised of a polymeric microsphere, preferably polystyrene/divinyl-benzene, containing carboxyl functional groups at least on its surface.
- (b) The solid support (a) where the solid support contains one or more fluorescent dyes in distinguishable ratios.
- (c) Solid support (b) where at least surface carboxyl groups have been modified with
20 a 4,7,10-trioxa-1,13-tridecanediamine linker.
- (d) Solid support (c) where the linker has been modified and/or contains the novel reactive group mono-fluoro squaric acid (MFS).

- (e) A biomolecule, specifically an oligonucleotide probe, containing a primary amine terminus.
 - (f) Spontaneous, covalent coupling of solid support (d) and biomolecule (e) to form a stable, covalent bond.
 - 5 (g) Use of the biomolecule-coupled solid support (f) in a single or multiplexed DNA assay.
-

Example 6.3.2

- 10 This example relates to, but is not limited to, the use of functionalized, or pre-activated, microspheres for covalent immobilization of biomolecules.

- (a) A solid support comprised of a polymeric microsphere, preferably polystyrene/divinyl-benzene, containing carboxyl functional groups at least on its surface.
- 15 (b) The solid support (a) where the solid support contains one or more fluorescent dyes in distinguishable ratios.
- (c) Solid support (b) where at least surface carboxyl groups have been modified with a cystamine linker.
- (d) Solid support (c) where the linker has been modified and/or contains the novel
20 vinyl sulfone (VS) reactive group.
- (e) A biomolecule, specifically an antibody, containing a primary amine or thiol.
- (f) Spontaneous, covalent coupling of solid support (d) and biomolecule (e) to form a stable, covalent bond.

- (g) Use of the biomolecule-coupled solid support (f) in a single or multiplexed immunoassay.

Example 6.3.3

5

This example relates to, but is not limited to, the use of functionalized, or pre-activated, microspheres for covalent immobilization of biomolecules.

- 10 a) A solid support comprised of a polymeric microsphere, preferably polystyrene/divinyl-benzene, containing carboxyl functional groups at least on its surface.
- b) The solid support (a) where the solid support contains one or more fluorescent dyes in distinguishable ratios.
- c) Solid support (b) where the carboxyl groups have been modified to contain the novel tetra-fluoro-sulfophenyl ester (TFS) reactive group.
- 15 d) A biomolecule, specifically an antigen, containing a primary amine.
- e) Spontaneous, covalent coupling of solid support (c) and biomolecule (d) to form a stable, covalent bond.
- f) Use of the biomolecule-coupled solid support (e) in a single or multiplexed immunoassay.

20

Example 6.3.4

This example relates to, but is not limited to, the use of a solid surface for covalent immobilization of functionalized, or pre-activated biomolecules.

5

- a) A two-dimensional solid support comprised of quartz, and containing hydroxyl functional groups at least on its surface.
- b) Solid support (a) where at least surface hydroxyl groups have been modified with aminopropyl-triethoxy silane, an amino-terminated silane linker.
- 10 c) A biomolecule, specifically an oligonucleotide, where the terminus has been modified to contain the novel reactive group mono-fluoro squaric acid (MFS).
- d) Spontaneous, covalent coupling of solid support (b) and biomolecule (c) to form a stable, covalent bond.
- e) Use of the biomolecule-coupled solid support (d) in a single or multiplexed DNA
15 assay.

Example 6.3.5

This example relates to, but is not limited to, the use of functionalized, or pre-activated,
20 microspheres for covalent immobilization of semi-conductor nanoparticles.

- a) A solid support comprised of a polymeric microsphere, preferably polystyrene/divinyl-benzene, containing carboxyl functional groups at least on its surface.

- b) Solid support (a) where the carboxyl groups have been modified to contain the novel vinyl sulfone (VS) reactive group.
- c) One or more semi-conductor nanoparticles having one or more distinguishable fluorescence emissions or wavelengths.
- 5 d) Semi-conductor nanoparticles (c) having at least thiol functional groups at least on the surface of the particles.
- e) Spontaneous, covalent coupling of solid support (b) and semi-conductor nanoparticles (d) to form a stable, covalent bond.
- f) Use of the semi-conductor nanoparticles -coupled solid support (e) for decoding
10 in a single multiplexed assay.

Example 6.3.6

This example relates to, but is not limited to, the covalent coupling of functionalized, or
15 pre-activated, microspheres to functionalized, or pre-activated nanospheres using a linker or bridge between the two particles.

- a) A solid support comprised of a polymeric microsphere, preferably polystyrene/divinyl-benzene, containing carboxyl functional groups at least on its surface.
- 20 b) Solid support (a) where the carboxyl groups have been modified to contain the novel mono-fluoro squaric acid (MFS) reactive group.

- c) Solid support (b) where the novel mono-fluoro squaric acid (MFS) reactive group has been modified with the bifunctional linker 4,7,10-trioxa-1,13-tridecanediamine.
- d) A second solid support comprised of polymeric nanospheres, preferably polystyrene/ divinyl-benzene, containing carboxyl functional groups at least on its surface.
- e) Solid support (d) where the carboxyl groups have been modified to contain the novel mono-fluoro squaric acid (MFS) reactive group.
- f) Solid support (e) having one or more fluorescent dyes in distinguishable ratios.
- g) Spontaneous, covalent coupling of microsphere solid support (c) and nanosphere solid support (f) to form a stable, covalent bond.
- h) Use of the nanosphere-coupled microsphere solid support (g) for decoding in a single or multiplexed assay.

Example 6.3.7

This example relates to, but is not limited to, the use of functionalized, or pre-activated, microspheres for covalent immobilization of dendrimers.

- a) A solid support comprised of a polymeric microsphere, preferably polystyrene/ divinyl-benzene, containing carboxyl functional groups at least on its surface.
- b) The solid support (a) where the solid support contains one or more fluorescent dyes in distinguishable ratios.

- c) Solid support (b) where the carboxyl groups have been modified to contain the novel tetra-fluoro-sulfo-phenyl ester (TFS) reactive group.
- d) A dendrimer containing primary amine functional groups.
- e) Spontaneous, covalent coupling of solid support (c) and dendrimer (d) to form a
5 stable, covalent bond.
- f) Modification of the dendrimer-coupled solid support (e) with a bifunctional linker containing the novel reactive group mono-fluoro squaric acid (MFS) on both termini of the linker.
- g) A biomolecule, specifically an antibody, containing a primary amine.
- 10 h) Spontaneous, covalent coupling of solid support (f) and biomolecule (g) to form a stable, covalent bond.
- i) Use of the biomolecule-coupled solid support (h) in a single or multiplexed immunoassay.

15 Example 6.3.8

This example relates to, but is not limited to, the covalent coupling of biomolecules to microspheres via a novel linker.

- 20 a) A solid support comprised of a polymeric microsphere, preferably polystyrene/divinyl-benzene, containing carboxyl functional groups at least on its surface.
- b) The solid support (a) where the solid support contains one or more fluorescent dyes in distinguishable ratios.

- c) Solid support (b) where at least surface carboxyl groups have been modified with a novel bifunctional amine termini linker containing a least one or more squaric acid functional groups within the linker chain.
- d) A biomolecule, specifically an oligonucleotide probe, containing the novel tetra-
5 fluoro-sulfophenyl ester (TFS) reactive group at one terminus.
- e) Spontaneous, covalent coupling of solid support (c) and biomolecule (d) to form a stable, covalent bond.
- f) Use of the biomolecule-coupled solid support (e) in a nucleic acid-based assay, wherein said assay comprises DNA, RNA, PNA, etc.

10

Example 6.3.9

This example relates to, but is not limited to, the covalent labeling of a biomolecule with a functionalized, or pre-activated fluorophore.

15

- a) A fluorophore functionalized, modified and/or synthesized to contain the novel reactive group mono-fluoro squaric acid (MFS).
- b) A biomolecule, specifically avidin, streptavidin, neutra-avidin and the like containing primary amines.
- c) Spontaneous, covalent labeling of biomolecule (b) and the pre-activated
20 fluorophore (a) to form a stable, covalent bond.
- d) A solid support comprised of a polymeric microsphere, preferably polystyrene divinyl-benzene, containing biotin functional groups at least on its surface.

- e) The solid support (d) where the solid support contains one or more fluorescent dyes in distinguishable ratios.
- g) Use of the solid support (e) in a single or multiplexed assay where the fluorophore-labeled biomolecule (c) is used as a reporter molecule.

5

Example 6.3.10

This example relates to, but is not limited to, the use of functionalized, or pre-activated, biomolecules for the covalent immobilization onto a solid surface.

10

- a) A solid support comprised of one or more metals.
- b) The solid support (a) where the solid support has been modified with a self-assembled monolayer (SAM) to contain thiol functional groups.
- c) A biomolecule, specifically an oligonucleotide, modified and/or synthesized to
- 15 contain the novel reactive group vinyl sulfone (VS) at one terminus.
- d) Spontaneous, covalent coupling of solid support (b) and biomolecule (c) to form a stable, covalent bond.
- e) Use of the biomolecule-coupled solid support (d) in a single or multiplexed nucleic acid-based assay, wherein said assay comprises DNA, RNA, PNA, etc.

20

Example 6.3.11

This example relates to, but is not limited to, the use of functionalized, or pre-activated, particles for the covalent immobilization of fluorophores.

- a) Solid support particles comprised of one or more metals.
- 5 b) The solid support (a) where the solid support has been modified to contain the novel functional group mono-fluoro squaric acid (MFS).
- c) J- or H- aggregate fluorophores containing amines and a quencher molecule.
- d) Spontaneous, covalent coupling of solid support (b) and fluorophore (c) to form a stable, covalent bond.
- 10 e) Use of the fluorophore-labeled particles (d) as a reporter in a single or multiplexed assay.

7.0 Examples of Synthetic Procedures for Preparing the Novel Reactive Groups

Aspects of the invention include materials and procedures for preparing
15 compositions, conjugates and/or mixtures involving polymer particles, various linkers and functional groups. These linkers and functional groups are described as follows:
(5.0) synthetic procedures of surface functional groups and spacers, (5.1) evaluation of novel reactive groups, (5.2) examples of coupling procedures. Such descriptions provided herein are not intended to limit the present invention in any way.

20

7.0.1. Sulfonyl Chloride

The following describes a method for the preparation of an activated surface capable of immobilizing a biomolecule in accordance with the present invention. In

particular, the following example describes a method for activating carboxylated polystyrene microspheres with sulfonyl chloride groups.

100 μ L (approximately 11 million microspheres) of a carboxylated polystyrene microsphere solution (5.5 μ m) was washed once with 250 μ L of DI water, three times
5 with 250 μ L of methanol, and three times with 250 μ L of benzene using centrifugation at 13,400 x g for 1 minute to pellet and 20 seconds of sonication to resuspend the microspheres. Finally they were suspended in 250 μ L of benzene, 50 μ L of thionyl chloride was added and the microspheres were heated at 40 °C for 2 hours. Then the microspheres were washed two times with 250 μ L of benzene and dried under reduced
10 pressure (< 5 torr) for 2 hours. They were suspended in a solution of potassium 7-amino-1,3-disulfonylnaphthalene in 200 μ L of pyridine and kept at room temperature for 4 hours. Then they were washed two times with 250 μ L of pyridine, four times with 250 μ L of DI water, two times with 250 μ L of methanol, and two times with 250 μ L of benzene and suspended in a solution of 50 μ L thionyl chloride and 25 μ L of
15 dimethylformamide (DMF) in 250 μ L of benzene and kept at room temperature for 20 minutes and at 40 °C for one hour. Afterwards the reactive microspheres were washed once with 250 μ L of benzene and three times with 250 μ L of acetonitrile and stored in acetonitrile until used. The just described procedure is graphically described in Entry 1c of Table 1.

20

7.0.2. Sulfonyl Fluoride

The following describes a method for the preparation of an activated surface capable of immobilizing a biomolecule in accordance with the present invention. In

particular, the following example describes a method for activating carboxylated polystyrene microspheres with sulfonyl fluoride groups.

300 μL (32 million microspheres) of a carboxylated polystyrene microsphere solution (5.5 μm) was washed two times with 500 μL of DI water, two times with 500 μL of methanol, and two times with 500 μL of benzene using centrifugation at 13,400 x g for 1 minute to pellet the microspheres and 20 seconds of sonication to resuspend the microspheres. The microspheres were then suspended in a solution of 50 μL thionyl chloride in 250 μL of benzene and kept at 40 °C for 2 h. Then they were washed three times with 500 μL of benzene and two times with 500 μL of acetonitrile and afterwards suspended in a solution of 12 mg of potassium 7-amino-1,3-disulfonylnaphthalene in 500 μL of acetonitrile and placed in a shaker at room temperature. After 14 hours the microspheres were washed two times with 500 μL of acetonitrile. The microspheres were suspended in a solution of acetonitrile containing 15 μL of cyanuric fluoride and 20 μL of pyridine and kept at -15 °C for 14 h and afterwards washed three times with 500 μL of acetonitrile. The microspheres were suspended and stored in 1mL of acetonitrile. The just described procedure is graphically described in Entry 2b of Table 1.

7.0.3. Mono-fluoro Squaric Acid (MFS)

The following describes a method for the preparation of an activated surface capable of immobilizing a biomolecule in accordance with the present invention. In particular, the following example describes a method for activating carboxylated polystyrene microspheres with mono-fluoro squaric acid groups using adipic acid dihydrazide as a linker.

300 μL (32 million microspheres) of a carboxylated polystyrene microsphere solution (5.5 μm) was washed three times with 500 μL of a solution containing 0.01% Tween 20 and 0.1 M MES buffer, pH 6.0 using centrifugation at 13,400 x g for 1 minute to pellet the microspheres and 20 seconds of sonication to resuspend the microspheres.

5 The microspheres were then suspended in 500 μL of a solution containing 32 mg/mL of ADH (adipic acid dihydrazide) and 2 g/mL of EDC, 0.01% Tween 20, and 0.1 M MES buffer, pH 6.0 and placed on a rotating mixer for 2 hours protected from light. The microspheres were washed three times with 500 μL of water, three times with 500 μL of methanol, and three times with 500 μL of benzene. The microspheres were then

10 suspended in 500 μL of benzene and 1 μL of dibutoxy cyclobutene dione was added. After shaking on a thermal shaker for 14 hours at 25 $^{\circ}\text{C}$, the microspheres were washed three times with 500 μL of benzene, three times with 500 μL of methanol, and three times with 500 μL of DI water. To the microspheres was added 500 μL of a 1 M solution of sodium hydroxide. The microspheres were then placed in a thermal shaker for 2 hours at

15 60 $^{\circ}\text{C}$. Then they were washed with 500 μL of methanol to recover the microspheres. The microspheres were then washed with 500 μL of a 2 M solution of hydrochloric acid. Methanol was added to recover the microspheres. The microspheres were then washed three times with 500 μL of methanol and three times with 500 μL of acetonitrile. The microspheres were then suspended in 500 μL of acetonitrile. A solution of 15 μL of

20 cyanuric fluoride and 20 μL of pyridine was added and then the microspheres were stored at -15 $^{\circ}\text{C}$ for 14 hours. The microspheres were then washed three times with 500 μL of acetonitrile. The microspheres were suspended and stored in 1 mL of acetonitrile. The just described procedure is graphically described in Entry 3c of Table 1.

7.0.4. Cyanuric Fluoride

The following describes a method for the preparation of an activated surface capable of immobilizing a biomolecule in accordance with the present invention. In particular, the following example describes a method for activating carboxylated polystyrene microspheres with cyanuric fluoride using 1,6-diaminohexane as a linker.

300 μ L (32 million microspheres) of carboxylated polystyrene microsphere solution (5.5 μ m) was washed three times with 500 μ L of a solution containing 0.01% Tween 20 and 0.1 M MES buffer, pH 6.0 using centrifugation at 13,400 x g for 1 minute to pellet the microspheres and 20 seconds of sonication to resuspend the microspheres. Afterwards they were suspended in 500 μ L of a solution containing 32 mg/mL of 1,6-diaminohexane and 2 g/mL of EDC, 0.01% Tween 20, and 0.1 M MES buffer, pH 6.0 and placed on a rotating mixer for 2 hours protected from light. Subsequently the microspheres were washed three times with 500 μ L of water, three times with 500 μ L of methanol, and three times with 500 μ L of acetonitrile. The microspheres were then suspended in a solution containing 500 μ L of acetonitrile, 20 μ L of trimethyl amine and 15 μ L of cyanuric fluoride and was set for 14 hours at -15 °C. Finally they were washed three times with acetonitrile. The microspheres were suspended and stored in 1 mL of acetonitrile. The just described procedure is graphically described in Entry 4 of Table 1.

7.0.5. Vinyl Sulfone (VS)

The following describes a method for the preparation of an activated surface capable of immobilizing a biomolecule in accordance with the present invention. In particular, the following example describes a method for activating carboxylated polystyrene microspheres with vinyl sulfone (VS) using 2-aminoethanethiol as a linker.

5 300 μ L (32 million microspheres) of a carboxylated polystyrene microsphere solution (5.5 μ m) was washed three times with 500 μ L of 0.1 M MES buffer, pH 6.0 incl. 0.01% Tween 20 using centrifugation at 13,400 x g for 1 minute to pellet the microspheres and 20 seconds of sonication to resuspend the microspheres. Subsequently the microspheres were suspended in 500 μ L of a 16 mg/mL solution of cysteamine and
10 30 mg/mL solution of EDC in 0.01% Tween 20, 0.1 M MES buffer, pH 6.0 and placed on a rotating mixer protected from light for 2 hours. The microspheres were washed three times with 500 μ L of water and three times with 500 μ L of 0.1M sodium chloride/0.1 M sodium acetate buffer, pH 4.5. The disulfide bonds of the bound cysteamine groups were reduced by suspending the microspheres in 500 μ L of a 11 mg/mL solution of
15 dithiothreitol (DTT) in 0.1 M sodium acetate/0.1 M sodium chloride buffer, pH 4.5. The microspheres were placed on a rotating mixer for 30 minutes and afterwards washed three times with 500 μ L of methanol. Then they were suspended in 500 μ L of dichloromethane and 5 μ L of vinyl sulfone (VS) was added. After mixing on a rotating mixer for 14 hours, 500 μ L of methanol was added and the microspheres were recovered
20 and washed three times with 500 mL of methanol. The microspheres were suspended and stored in 1mL of methanol. The just described procedure is graphically described in Entry 5b of Table 1.

7.0.6. Protected Vinyl Sulfone

The following describes a method for the preparation of an activated surface capable of immobilizing a biomolecule in accordance with the present invention. In particular, the following example describes a method for converting the activated polystyrene microspheres of the previous example into a more hydrolysis resistant form.

Microspheres prepared according to Example 5.0.5 were suspended in 800 μ L of a solution containing 3 mg of sodium thiosulfite, 0.01% Tween 20, and sodium phosphate buffer, pH 4.0 for 14 hours. The microspheres were washed three times with 500 μ L of DI water. The microspheres were suspended and stored in 1 mL of DI water. The microspheres are not reactive with nucleophiles unless they are first treated with a buffer of pH 9-10. The just described procedure is graphically described in Entry 5c of Table 1.

7.0.7. Tetra-fluoro sulfo-phenyl Ester (TFS)

The following describes a method for the preparation of an activated surface capable of immobilizing a biomolecule in accordance with the present invention. In particular, the following example describes a method for directly activating carboxylated polystyrene microspheres with tetra-fluoro sulfophenyl esters.

300 μ L (32 million microspheres) of a carboxylated polystyrene microsphere solution (5.5 μ m) was washed three times with 500 μ L of a solution containing 0.01% Tween 20 and 0.1 M MES buffer, pH 6.0 using centrifugation at 13,400 x g for 1 minute to pellet and 20 seconds of sonication to resuspend the microspheres. Then they were suspended in 500 μ L of a solution containing 24 mg/mL of 2,3,5,6 tetrafluorophenol-4-

sulfate (synthesized from 2,3,5,6 tetrafluorophenol according to the procedure of Gee, K.R. et al. *Tetrahedron Lett.*, 1999, 40, 1472-1474), 220 mg/mL of EDC, 0.01% Tween 20, and 0.1 M MES buffer, pH 6.0 and then placed on a rotating mixer protected from light for 2 hours. The microspheres were washed three times with 500 μ L of DI water. The microspheres were suspended and stored in 1 mL of DI water. The just described procedure is graphically described in Entry 6 of Table 1.

7.1. Examples of Novel Reactive Group Evaluation

In order to quantify the reactivity of the different novel reactive functional groups on polystyrene microspheres, a simple assay was developed using a biotin-amine derivative. First, biotin-LC-PEO-amine (obtained from Pierce, Rockford, IL) was coupled to carboxylated microspheres using typical EDC-mediated methods, followed by reaction with streptavidin-PE. The optimum concentrations of both biotin-amine and streptavidin-PE (obtained from Molecular Probes, Eugene, OR) were titrated. This coupling assay provided a "standard" by which to measure and compare the reactivity of microspheres modified with the novel reactive functional groups. The modified microspheres are evaluated by reacting the biotin-amine directly, followed by reaction with streptavidin-PE. Functional group stability was evaluated by storing the microspheres either in buffer (pH 6; 4 °C) or dry, and performing the biotin-LC-PEO-amine assay at set intervals (e.g., days, weeks, months, etc.).

According to our test results our new novel reactive groups exhibit very desirable properties. For example, novel reactive groups show good reactivity with nucleophilic compounds, have substantially improved stability in aqueous media, form stable

conjugates, require no additional activating reagents (e.g., EDC and/or NHS esters), and may provide more specific conjugation (i.e., reduce non-specific interaction/binding with solid substrates) thus protecting the integrity of biomolecules.

5 7.1.1 Coupling Reactivity and Reproducibility

An accelerated stability study comparing the EDC-mediated coupling method to mono-fluoro squaric acid (MFS)-modified microspheres was carried out over an equivalent of 350 days. Using the biotin-amine model assay, results showed comparable reactivity between the two methods. Results also show the mono-fluoro squaric acid
10 (MFS)-modified microspheres provide more reproducible coupling day-to-day. As depicted in Figure 1, the EDC coupling method showed 20% changes in coupling throughout the entire experiment. During the equivalent 350 days, the mono-fluoro squaric acid (MFS)-modified microspheres lost some activity gradually, retaining 80% activity at the end of the study (i.e., the greatest change in activity was shown at the end
15 of 350 equivalent days). Improvements in storage procedures are expected to eliminate any loss of activity for modified microspheres.

7.1.2 Stability

Results show that microspheres modified with novel reactive groups have
20 substantially improved stability in aqueous media. Figure 2 depicts an example of the stability of vinyl-sulfone (VS)-functionalized microspheres in buffer for at least 30 days. This is a substantial improvement compared to EDC and NHS reagents, however, since there is a trade-off between reactivity and stability, we have also evaluated various drying

and storage methods for long-term storage (including for example, 6 months, \geq approximately 6 months, greater than six months, six months to nine months, six months to one year, six months to two years, etc.) of the modified microspheres. Figures 3-6 depict examples of dry storage condition stability studies. Storage vessels that provide superior moisture barrier properties to those used in this study, will prevent loss of activity over time.

7.1.3 Bioassays

The performance of modified microspheres in real assays compared to the COOH microsphere-EDC method was evaluated. Figure 7 shows a coupling titration of an amino-modified DNA probe on COOH-functionalized microspheres (EDC-mediated reaction) vs. pre-activated microsphere method. Both coupling titrations were performed at 25°C. The DNA compliment target concentration for the assay was 20 fmoles at a hybridization temperature of 55°C. Results show the COOH-EDC method yields a non-linear response to the amount of probe coupled to the microsphere. The pre-activated microsphere probe titration is more linear, suggesting a more specific coupling of the probe. Both results are reproducible. Note: 25°C is not an optimal coupling temperature for the pre-activated microspheres. The signal is expected to improve with optimization of coupling temperature, as well as other parameters.

7.2 Examples of Coupling Procedures

7.2.1. Biotin-LC-PEO Amine

Surface-modified microspheres were washed three times with phosphate buffer (pH 6, 100 mM) and counted. 2.5×10^7 microspheres were aliquoted and washed once with phosphate buffer (pH 8, 100 mM). A solution of PEO-LC-biotin-amine (17.4 mg/mL) was prepared in phosphate buffer (pH 8, 100 mM). 100 μ L of this solution was
5 added to the microspheres, in 900 μ L phosphate buffer (pH 8, 100 mM). The suspension was incubated at 37 °C for 1 hour. After the reaction was complete, the microspheres were washed three times with PBS-TBN (phosphate buffered saline, pH 7.4 with 0.02% Tween 20 and 1g/L bovine serum albumin), and recounted. A suspension of 100,000 microspheres/mL PBS-TBN was reacted with 1 μ g Streptavidin-PE for 1 hour at room
10 temperature. Subsequently the microspheres were washed three times and resuspended in 1 mL PBS-TBN. The fluorescence intensity of the microspheres was analyzed on a Luminex 100™ instrument.

7.2.2. Biotinylated IgG









15 A suspension of 25×10^6 surface-modified microspheres was washed with 1 mL carbonate buffer (pH 9, 100 mM). A 1 mL solution of IgG (50 μ g/mL in 0.1 M pH 9 carbonate buffer) was added to the microspheres, vortexed, sonicated and incubated at 37 °C for 1 hour. After 1 hour, the sample was washed with 1 mL PBS-TBN (phosphate buffered saline, pH 7.4 with 0.02% Tween 20 and 1g/L bovine serum albumin). A
20 suspension of 100,000 microspheres/mL PBS-TBN was reacted with 1 μ g Streptavidin-PE for 1 hour at room temperature. Subsequently the microspheres were washed three times and resuspended in 1 mL PBS-TBN. The fluorescence intensity of the microspheres was analyzed on a Luminex 100™ instrument.


7.2.3. Biotinylated Oligonucleotides


5 x 10⁶ surface-modified microspheres were dispensed into a 1.5 ml centrifuge tube and washed with 1 mL of carbonate buffer (pH 9, 100 mM). 50 µL carbonate buffer (pH 9, 100 mM) was added to the microspheres. 1 µL of a 1 mM solution of amino-modified oligonucleotide was added and the suspension was incubated at 37 °C for 1 hour. After 1 hour the sample was washed with PBS-TBN. A suspension of 100,000 microspheres/mL PBS-TBN was reacted with 1 µg Streptavidin-PE for 1 hour at room temperature. Subsequently the microspheres were washed three times and resuspended in 1 mL PBS-TBN. The fluorescence intensity of the microspheres was analyzed on a Luminex 100™ instrument.

Those skilled in the art will recognize, or be able to ascertain using no more than routine experimentation, many equivalents to the specific embodiments of the invention described herein. Such equivalents are intended to be encompassed by the following claims.

TABLE 1. Summary of Functional Groups and Synthetic Routes to Functionalized Microspheres

1a	 
1b	 
1c	 
1d	 
















Table 2. Summary of Representative Linker Groups R_n


1.	$-X-CH_2CH_2O-(CH_2)_mX- \quad X=NH,S,O,Si,\overset{\overset{O}{\parallel}}{C} \quad n=0-500, m=0-5$
2.	$-E_1-CF_2-CF_2O-(CH_2)_mE_2- \quad E_1,E_2=NH,S,O,Si,\overset{\overset{O}{\parallel}}{C} \quad n=0-500, m=0-5$
3.	$-E_1-(CH_2CH_2)-N\begin{matrix} (CH_2)_2O(CH_2)_2E_2 \\ (CH_2)_2O(CH_2)_2E_3 \end{matrix}- \quad E_1, E_2, E_3=NH,S,O, Si, \overset{\overset{O}{\parallel}}{C}, PO_4$
4.	$-E_1-CH_2CH_2CH_2CH_2E_2- \quad E_1, E_2=NH,S,O,Si,\overset{\overset{O}{\parallel}}{C} \quad n=0-25$
5.	$-E_1-CH_2CH_2N(CH_2)_mE_2- \quad E_1, E_2=NH,S,O,Si, \overset{\overset{O}{\parallel}}{C} \quad n=0-500, m=0-5$
6.	$-HNHN\overset{\overset{O}{\parallel}}{S}NHNH-$
7.	$-HNHN\overset{\overset{O}{\parallel}}{S}OCH_2CH_2CH_2CH_2\overset{\overset{O}{\parallel}}{S}NHNH- \quad n=0-10$
8.	$-HNHN\overset{\overset{O}{\parallel}}{C}OCH_2CH_2CH_2CH_2\overset{\overset{O}{\parallel}}{C}NHNH- \quad n=0-10$
9.	
10.	$-C(=O)(CH_2)_n-C(=O)NHN\overset{\overset{O}{\parallel}}{S}NHN-C(=O)(CH_2)_n-C(=O)- \quad n=0-10$

11.	 $n=0-5$
12.	 $n=1-5$
13.	 $n=0-6$
14.	 <p>and other amino terminated dendritic structures</p>
15.	 <p>and other carboxy terminated dendritic structures</p>
16.	 $n = 0-20$
17.	 $n = 1 - 30$ <p>R_n = groups needed to form various natural and unnatural amino acids</p>


Claims

We claim:


1. A conjugate composition comprising one or more, in any combination, of Structures 1-6:




1




2




3



4



5



6

wherein:

n is 0, 1, 2, or 3;

X and Y are oxygen and/or sulfur in any combination;

X₂ and X₃ are chlorine or fluorine;

Y_2 is nitrogen or carbon;

arom is a substituted or unsubstituted phenyl, naphthyl or other polycyclic aromatic ring structure;

Z is chloride, fluoride, 2,3,5,6-tetrafluoro-4-sulfo-phenoxide, N-hydroxysuccinimide or other electrophilic group; and

R_1 - R_6 comprise hydrocarbon linker groups containing from 2-1000 atoms, optionally containing one or more halogen or heteroatoms selected from the group consisting of O, N, Si, P and S;

wherein said one or more, in any combination, of Structures 1-6 are connected through

10 their respective linker groups, R_1 - R_6 , to at least one entity B, wherein B is:

- (a) a 2-D film or substrate;
- (b) a micro- or nano- particle of any size or shape composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal, semiconductor particle, semiconductor nanocrystal, 15 magnetic particle, fullerene, nanotube, or any combination thereof;
- (c) an enzyme, antibody, protein, DNA, RNA, nucleotide, PNA, carbohydrate, fatty acid, lectin, peptide, receptor, dendrimer, cell, bacteria, virus, whole prokaryotic or eukaryotic organism, synthetic or natural membrane, biotin, hapten, organic monomer or polymer, or any 20 combination thereof;
- (d) a chromophore, fluorophore, bio- or chemi-luminescent compound, J or H aggregate, or any combination thereof;

(e) one or more of Structures 1-6, in any combination, connected through their respective linker groups R_1 - R_6 ; or any combination thereof.

- 5 2. The composition of Claim 1 wherein linker groups R_1 - R_6 are straight or branched chains, rings, or combinations thereof.
3. The composition of Claim 1 wherein R_1 - R_6 contain 2-100 atoms
- 10 4. The composition of Claim 1 wherein R_1 - R_6 contain 2-10 atoms.
5. The composition of Claim 1 wherein B is a polymeric microsphere.
6. The composition of Claim 5 wherein said polymeric microsphere comprises
15 polystyrene/divinyl benzene and carboxyl functional groups at least on its surface.
7. The composition of Claim 6 wherein said microsphere further comprises one or more fluorescent dyes in differing, distinguishable molar amounts.
- 20 8. A composition of Claim 1 comprising Structure 1.
9. The composition of Claim 8 wherein R_1 contains 2-100 atoms.

10. The composition of Claim 8 wherein R_1 contains 2-10 atoms.

11. A composition of Claim 8 in which Structure 1 is connected through its linker group R_1 to an entity B, wherein B is

- 5 (a) a 2-D film or substrate;
- (b) a micro- or nano- particle of any size or shape composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal, semiconductor particle, semiconductor nanocrystal, magnetic particle, fullerene, nanotube, or any combination thereof;
- 10 (c) an enzyme, antibody, protein, DNA, RNA, nucleotide, PNA, carbohydrate, fatty acid, lectin, peptide, receptor, dendrimer, cell, bacteria, virus, whole prokaryotic or eukaryotic organism, synthetic or natural membrane, biotin, hapten, organic monomer or polymer, or any combination thereof;
- 15 (d) a chromophore, fluorophore, bio- or chemi-luminescent compound, J or H aggregate, or any combination thereof;
- (e) one or more of Structures 1-6 connected through their linker groups R_1 - R_6 ;
- or
- any combination thereof.

20

12. The composition of Claim 10 wherein entity B is a polymeric microsphere.

13. The composition of Claim 11 wherein the polymeric microsphere comprises polystyrene/divinyl benzene and carboxyl functional groups at least on its surface.
14. The composition of Claim 12 wherein said microsphere further comprises one or
5 more fluorescent dyes in differing, distinguishable molar amounts.
15. A conjugate composition of Claim 1 in which Structure 2 is connected through its linker group R_2 to a solid support B, wherein the solid support B is
- (a) a 2-D film or substrate; or
 - 10 (b) a micro- or nano- particle of any size or shape composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal, semiconductor particle, semiconductor nanocrystal, magnetic particle, fullerene, nanotube, or any combination thereof.
- 15 16. The composition of Claim 14 wherein solid support B is a polymeric microsphere.
17. The composition of Claim 15 wherein the polymeric microsphere comprises polystyrene/divinyl benzene and carboxyl functional groups at least on its surface.
- 20 18. The composition of Claim 16 wherein said microsphere further comprises one or more fluorescent dyes in differing, distinguishable molar amounts.

19. A conjugate composition of Claim 1 in which Structure 3 is connected through its linker group R_3 to a solid support B, wherein the solid support B is
- (a) a 2-D film or substrate; or
 - (b) a micro- or nano- particle of any size or shape composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal, semiconductor particle, semiconductor nanocrystal, magnetic particle, fullerene, nanotube, or any combination thereof.
20. The composition of Claim 19 wherein solid support B is a polymeric microsphere.
21. The composition of Claim 20 wherein the polymeric microsphere comprises polystyrene/divinyl benzene and carboxyl functional groups at least on its surface.
22. The composition of Claim 21 wherein said microsphere further comprises one or more fluorescent dyes in differing, distinguishable molar amounts.
23. A conjugate composition of Claim 1 in which Structure 4 is connected through its linker group R_4 to a solid support B, wherein X_2 is chlorine or fluorine, wherein the solid support B is
- (a) a 2-D film or substrate; or

- (b) a micro- or nano- particle of any size or shape composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal, semiconductor particle, semiconductor nanocrystal, magnetic particle, fullerene, nanotube, or any combination thereof.

5

24. The composition of Claim 23 wherein solid support B is a polymeric microsphere.

25. The composition of Claim 24 wherein the polymeric microsphere comprises polystyrene/divinyl benzene and carboxyl functional groups at least on its surface.

10

26. The composition of Claim 25 wherein said microsphere further comprises one or more fluorescent dyes in differing, distinguishable molar amounts.

15

27. A conjugate composition of Claim 1 in which Structure 5 is connected through its linker group R_3 to a solid support B, wherein X_3 is chlorine or fluorine, Y_2 is nitrogen or carbon, and wherein the solid support B is

- (a) a 2-D film or substrate; or
- (b) a micro- or nano- particle of any size or shape composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal, semiconductor particle, semiconductor nanocrystal, magnetic particle, fullerene, nanotube, or any combination thereof.

20

28. The composition of Claim 27 wherein solid support B is a polymeric microsphere.
29. The composition of Claim 28 wherein the polymeric microsphere comprises
5 polystyrene/divinyl benzene and carboxyl functional groups at least on its surface.
30. The composition of Claim 29 wherein said microsphere further comprises one or more fluorescent dyes in differing, distinguishable molar amounts.
- 10 31. A conjugate composition of Claim 1 in which Structure 6 is connected through its linker group R_6 to a solid support B, wherein aromatic group, arom, can be substituted or unsubstituted phenyl, naphthyl or other polycyclic aromatic rings, and wherein the solid support B is
- (a) a 2-D film or substrate; or
- 15 (b) a micro- or nano- particle of any size or shape composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal, semiconductor particle, semiconductor nanocrystal, magnetic particle, fullerene, nanotube, or any combination thereof.
- 20 32. The composition of Claim 31 wherein solid support B is a polymeric microsphere.

33. The composition of Claim 32 wherein the polymeric microsphere comprises polystyrene/divinyl benzene and carboxyl functional groups at least on its surface.
- 5 34. The composition of Claim 33 wherein said microsphere further comprises one or more fluorescent dyes in differing, distinguishable molar amounts.
35. A method for coupling two or more entities together, comprising:
- (a) providing one or more conjugate compositions of Claims 1 having one or
10 more, in any combination, of Structures 1-6 connected through their respective linker groups, R_1 - R_6 , to at least one entity B;
- (b) providing one or more nucleophile-containing entities comprised of:
- a 2-D film or substrate;
- a micro- or nano-particle of any size or shape, composed of organic
15 polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal, semiconductor particle, semiconductor nanocrystal, magnetic particle, fullerene, nanotube or any combination thereof;
- an enzyme, antibody, protein, DNA, RNA, nucleotide, PNA, carbohydrate, fatty acid, lectin, peptide, receptor, chromophore,
20 fluorophore, bio- or chemi-luminescent compound, J or H aggregate, cell, bacteria, virus, whole prokaryotic or eukaryotic organism, synthetic or natural membrane, biotin, hapten, organic monomer or polymer, or dendrimer, or any combination thereof; and

- (c) reacting said one or more conjugate compositions with said one or more nucleophile-containing entities to produce at least one entity B linked through one or more linker groups of Structures 1-6 to said one or more nucleophile-containing entities.

5

36. A method for the synthesis of compositions of Claim 1 wherein:

- (a) the one or more, in any combination, of Structures 1-6 of Claim 1 are conjugated to said entity B before the fabrication of said entity B;
- (b) the one or more, in any combination, of Structures 1-6 of Claim 1 are conjugated to said entity B during the fabrication of said entity B; or
- 10 (c) the one or more, in any combination, of Structures 1-6 of Claim 1 are conjugated to said entity B after the fabrication of said entity B.

37. A method of crosslinking one or more nucleophile-containing entities to at least one other entity comprising reacting a composition of Structure 1 of Claim 1, wherein:

- (a) n is 0, 1, 2, or 3
- (b) X and Y are oxygen and/or sulfur in any combination;
- (c) Z and R₁ are chloride; fluoride; 2,3,5,6-tetrafluoro-4-sulfo-phenoxide; N-hydroxysuccinimide; and similar electrophilic groups or any combination thereof;
- 20

with one or more nucleophile-containing entities, comprised of:

a 2-D film or substrate;

a micro- or nano-particle of any size or shape, composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal, semiconductor particle, semiconductor nanocrystal, magnetic particle, fullerene, nanotube or any combination thereof;

5 an enzyme, antibody, protein, DNA, RNA, nucleotide, PNA, carbohydrate, fatty acid, lectin, peptide, receptor, chromophore, fluorophore, bio- or chemiluminescent compound, J or H aggregate, cell, bacteria, virus, whole prokaryotic or eukaryotic organism, synthetic or natural membrane, biotin, hapten, organic monomer or polymer, or dendrimer, or any combination

10 thereof;

to provide one or more nucleophile-containing entities crosslinked to at least one other entity.

38. A bridge group composition comprising two or more of Structures 1-6 of Claim 1,

15 in any combination, joined together through their respective linker groups R₁-R₆, wherein said joining is one or more of end-to-end, branched, or dendritic, in any combination.

39. A method for crosslinking two or more nucleophile-containing entities

20 (a) providing one or more bridge group compositions of Claim 38;

(b) providing one or more nucleophile-containing entities comprised of:

a 2-D film or substrate;

- a micro- or nano-particle of any size or shape, composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite, inorganic crystal, semiconductor particle, semiconductor nanocrystal, magnetic particle, fullerene, nanotube or any combination thereof;
- 5 an enzyme, antibody, protein, DNA, RNA, nucleotide, PNA, carbohydrate, fatty acid, lectin, peptide, receptor, chromophore, fluorophore, bio- or chemi-luminescent compound, J or H aggregate, cell, bacteria, virus, whole prokaryotic or eukaryotic organism, synthetic or natural membrane, biotin, hapten, organic monomer or
- 10 polymer, or dendrimer, or any combination thereof; and
- (c) reacting said one or more bridge group compositions with said one or more nucleophile-containing entities to produce at least two crosslinked nucleophile-containing entities.

- 15 40. A bridge group composition comprising one or more of Structures 1-6 of Claim 1, in any combination, conjugated by their respective linker groups R_1 - R_6 to one or more nucleophilic groups, wherein if two or more of Structure 1-6 are joined together, they are joined together through their respective linker groups R_1 - R_6 , wherein said joining is one or more of end-to-end, branched, or dendritic, in any
- 20 combination.

41. A method for crosslinking one or more nucleophile-containing entities with one or more entities conjugated with one of more of Structures 1-6 of Claim 1, comprising:

- (a) providing one or more bridge group compositions of Claim 40;
- 5 (b) providing one or more of the compositions of Claim 1;
- (c) providing one or more nucleophile-containing entities comprised of:
 - a 2-D film or substrate;
 - a micro- or nano-particle of any size or shape, composed of organic polymer, MIPS, glass, metal, clay, resin, diatomaceous earth, zeolite,
 - 10 inorganic crystal, semiconductor particle, semiconductor nanocrystal, magnetic particle, fullerene, nanotube or any combination thereof;
 - an enzyme, antibody, protein, DNA, RNA, nucleotide, PNA, carbohydrate, fatty acid, lectin, peptide, receptor, chromophore, fluorophore, bio- or chemi-luminescent compound, J or H aggregate,
 - 15 cell, bacteria, virus, whole prokaryotic or eukaryotic organism, synthetic or natural membrane, biotin, hapten, organic monomer or polymer, or dendrimer, or any combination thereof; and
- (d) reacting said one or more bridge group compositions with said one or more nucleophile-containing entities and one or more compositions of
- 20 Claim 1 to produce at least two crosslinked entities.




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7